

Fashion color Fall 2011

Sun colours Disperse dyes

Pantone Inc. announced fashion colors Fall 2011 from New York fashion week. You can easily achieve the fashion colors according to below recipes. Please note that the recipes were formulated by color matching program, Not by actual dyeing. So you need to adjust recipes to be more close to the standard of pantone TCX. If you have any questions for recipes, please contact us.

	% o.w.f.
Suncron Yellow S-FW	0.087
Suncron G/Yellow S-3FW	0.124
Suncron Blue S-BG	0.022
	0.02 / 0.69 / 1.70

CMC DE / M.I.(1,2) / M.I.(1,3)
1st : F02, 2nd : A, 3rd : D65

Suncron Yellow 3GE 200%	0.065
Suncron Orange H3R 200%	0.046
Suncron Red F3BS 150%	0.086
	0.01 / 0.75 / 1.06

Suncron Yellow S-FW	0.089
Suncron G/Yellow S-3FW	0.047
Suncron Red S-XFW	0.134
	0.08 / 0.23 / 0.66

Suncron Yellow 3GE 200%	0.038
Suncron Red FB 200%	0.476
Suncron Violet FBL 200%	0.045
	0.03 / 0.63 / 0.93

Suncron Yellow S-FW	0.036
Suncron Crimson S-FW	0.532
Suncron Violet S-FW	0.006
	0.10 / 0.82 / 0.95

Suncron Yellow 3GE 200%	0.002
Suncron Red F3BS 150%	0.474
Suncron Blue 2RSE	0.241
	0.09 / 1.51 / 2.04

Suncron Red F3BS 150%	0.469
Suncron Blue 2RSE	0.244
	0.46 / 1.58 / 2.04

Suncron Yellow 3GE 200%	0.149
Suncron Scarlet G-S 200%	0.040
Suncron Blue FBL	0.104
	0.01 / 0.39 / 1.38

Suncron Yellow S-FW	0.145
Suncron Red CBN	0.065
Suncron Blue S-BG	0.104
	0.01 / 0.90 / 0.61

Suncron Yellow S-FW	0.238
Suncron Crimson S-FW	0.234
Suncron Blue S-2G	1.219
	0.02 / 0.09 / 0.42

Suncron Yellow S-FW	0.226
Suncron Red CBN	0.219
Suncron Blue S-2G	1.248
	0.03 / 0.20 / 0.30

Suncron Yellow 3GE 200%	0.270
Suncron Scarlet 2GE 200%	0.369
Suncron Blue FBL	0.361
	0.01 / 0.29 / 1.10

Suncron Yellow S-FW	0.417
Suncron Red S-BFW	0.457
Suncron Blue S-BG	0.335
	0.01 / 0.86 / 0.81

Suncron Yellow 3GE 200%	0.029
Suncron Scarlet 2GE 200%	0.035
Suncron Blue FBL	0.034
	0.01 / 0.59 / 0.89

Suncron Yellow SE-5G	0.036
Suncron Red S-XFW	0.022
Suncron Blue 3RSE	0.021
	0.02 / 0.89 / 0.53

Suncron Yellow 3GE 200%	0.002
Suncron Red FB 200%	0.013
Suncron Blue FBL	0.013
	0.01 / 0.14 / 0.16

Suncron Yellow S-FW	0.003
Suncron Crimson S-FW	0.013
Suncron Blue S-BG	0.013
	0.01 / 0.09 / 0.12

Suncron Yellow 3GE 200%	0.009
Suncron Scarlet 2GE 150%	0.017
Suncron Blue FBL	0.070
	0.01 / 0.16 / 0.74

Suncron Yellow S-FW	0.016
Suncron Red S-BFW	0.012
Suncron Blue S-BG	0.076
	0.01 / 0.67 / 0.31

NEW YORK
FASHION WEEK
FEBRUARY 10-17, 2011

Bamboo
14-0740 TCX

Emberglow
17-1547 TCX

Honeysuckle
18-2120 TCX

Phlox
19-2820 TCX

Cedar
16-0526 TCX

Deep Teal
19-4914 TCX

Coffee Liqueur
18-0930 TCX

Nougat
16-1320 TCX

Orchid Hush
13-3805 TCX

Quarry
15-4305 TCX



OHYOUNG INDUSTRIAL CO., LTD.

Head Office

6th Floor, SEMTOP-Building, 448-16,
Shingil-5dong, Yeongdeungpo-ku, Seoul,
Korea #150-851

www.ohyoung.com
ohyoung@ohyoung.net