

Grenadine 17-1558

	% o.w.f.	CMC DE	M.I.(1,2)
Sunfix Orange S2RN	1.5888	0.00	0.28
Sunfix Red SPR	1.5028		
Sunfix Blue SF-RL 200%	0.0016		
Sunfix Orange S2R 150%	0.8595	0.00	0.39
Sunfix Scarlet S2G 150%	1.4776		
Sunfix Blue SPR	0.0038		

Tawny Port 19-1725

Sunfix Yellow SPD conc.	1.5509	0.00	0.30
Sunfix Red SPD conc.	2.6475		
Sunfix Navy Blue SPD conc.	0.6057		
Sunfix Yellow SSR	1.0884	0.00	0.19
Sunfix Red SPD conc.	2.4595		
Sunfix Navy Blue SPD conc.	0.6188		

Ballet Slipper 13-2808

Sunfix Yellow SPR	0.0041	0.01	0.34
Sunfix Red SPR-F	0.0111		
Sunfix Blue SPR	0.0017		
Sunfix Yellow SPR	0.0044	0.00	0.46
Sunfix Red SPR	0.0108		
Sunfix Blue SPR	0.0033		

Butterum 16-1341

Sunfix Yellow SSR	0.2217	0.00	0.45
Sunzol Orange 3R	0.2013		
Sunfix Blue SPR	0.0427		

Navy Peony 19-4029

Sunfix Red SPR	0.3791	0.00	0.08
Sunfix Night SS	0.9439		
Sunfix Blue SSR	1.6007		
Sunfix Yellow SPR	0.1547	0.01	0.34
Sunfix Red SPR	0.1253		
Sunfix Blue SPR	4.1600		

	% o.w.f.	CMC DE	M.I.(1,2)
Sunfix Yellow SPR	0.1448	0.00	0.39
Sunfix Red SPR-F	0.0673		
Sunfix Blue SPR	0.1745		

Sunfix Yellow S4GL 200%	0.4825	0.00	0.32
Sunzol Turquoise Blue G 266%	0.8717		
Sunfron Blue SN-R	1.6954		

Sunfix Yellow S4GL 200%	0.4586	0.00	0.23
Suncion Blue H-ERD 125%	2.9906		
Sunzol Turquoise Blue G 266%	0.8097		

Sunfix Yellow S4GL 200%	0.9286	0.00	0.22
Sunfix Yellow SPD conc.	0.5299		
Sunfix Blue SPR	0.1295		

Sunfix Blue SSR	0.0605	0.34	0.59
Sunfix Royal Blue FE-FR	0.0293		
Sunzol Blue RS 150%	0.3352		

Sunfix Red FE-6BA	0.0084	0.42	0.71
Sunfix Blue SSR	0.2756		
Sunzol Blue RS 150%	0.1248		

Sunfix Yellow SS	3.2808	0.00	0.55
Sunfix Red SPR-F	0.3534		
Sunfix Blue SPR	0.0167		

Neutral Gray 17-4402

Shaded Spruce 19-4524

Golden Lime 16-0543

Marina 17-4041

Autumn Maple 17-1145

Head Office

6th Floor, SEMTOP-Building, 59, Singil-ro, Yeongdeungpo-gu, Seoul, Korea #150-851
ohyoung@ohyoung.net / www.ohyoung.com

* Reference

Please note these recipes were formulated by CCM program, NOT by the lab dyeing, so the accuracy of total recipes might be approximately 90% because of using different fabric and pretreatment between your conditions and ours.