

Disperse dyes	% o.w.f.	CMC DE	M.I.(1,2)	Disperse dyes	% o.w.f.	CMC DE	M.I.(1,2)
Suncron Yellow S-FW ECO	0.0584			Suncron Yellow Brown S-FW ECO	0.0272		
Suncron Turquoise Blue S-FW ECO	3.5600	0.02	0.20	Suncron Red S-BFW ECO	1.2585	0.03	0.43
Suncron Blue S-FBL 300% ECO	0.5976			Suncron Navy Blue S-XFW ECO	2.6135		
Suncron Yellow T-FW ECO	0.0691			Suncron G/Yellow S-3FW ECO	0.0326		
Suncron Turquoise Blue G-GL 200% ECO	3.2676	0.01	0.20	Suncron Red S-FW ECO	0.9905	0.03	0.48
Suncron Blue S-FBL 300% ECO	0.5389			Suncron Navy Blue S-XFW ECO	2.5212		
Suncron Yellow T-FW ECO	0.3976			Suncron Yellow Brown S-FW ECO	0.0977		
Suncron Orange T-FW ECO	0.0167	0.00	0.47	Suncron Red S-BFW ECO	0.0224	0.02	0.20
Suncron Blue T-FW ECO	0.0003			Suncron Navy Blue S-XFW ECO	0.2967		
Suncron Yellow T-FW ECO	0.3819			Suncron Yellow Brown S-FW ECO	0.1583		
Suncron G/Yellow S-3FW ECO	0.0157	0.01	0.46	Suncron Brill. Red S-FWH ECO	0.0502	0.01	0.23
Suncron Blue T-FW ECO	0.0013			Suncron Blue S-FWN ECO	0.4387		
Suncron Yellow T-FW ECO	0.2047			Suncron Yellow Brown S-FW ECO	1.8212		
Suncron Yellow Brown T-FW ECO	0.4471	0.06	0.36	Suncron Red CBN ECO	0.8292	0.01	0.27
Suncron Turquoise Blue S-FW ECO	1.4489			Suncron Blue S-FWN ECO	0.4437		
Suncron Yellow T-FW ECO	0.2339			Suncron Yellow T-FW ECO	0.5920		
Suncron Yellow Brown T-FW ECO	0.3584	0.06	0.47	Suncron Rubine T-FW ECO	0.8335	0.01	0.37
Suncron Turquoise Blue G-GL 200% ECO	1.2832			Suncron Navy Blue S-XFW ECO	0.2566		
Suncron Yellow Brown T-FW ECO	0.0832			Suncron Yellow E-3G 200% ECO	0.0014		
Suncron Rubine SE-CB 200% ECO	0.1339	0.05	0.48	Suncron Red E-FB 200% ECO	0.0027	0.01	0.32
Suncron Violet 3R ECO	1.2828			Suncron Blue E-FBL ECO	0.0016		
Suncron Crimson T-FW ECO	0.7964			Suncron Yellow RD-E ECO	0.0049		
Suncron Violet 3R ECO	0.5787	0.05	0.36	Suncron Red RD-E ECO	0.0054	0.01	0.28
Suncron Blue S-FWN ECO	0.0122			Suncron Blue RD-E ECO	0.0017		
Suncron G/Yellow S-3FW ECO	0.0112			Suncron Yellow E-3G 200% ECO	0.0315		
Suncron Brill. Scarlet S-FW ECO	0.0532	0.06	0.81	Suncron Red E-FB 200% ECO	0.0539	0.01	0.77
Suncron Blue S-FWN ECO	0.0015			Suncron Blue E-FBL ECO	0.1283		
Suncron Orange T-FW ECO	0.0182			Suncron Yellow Brown T-FW ECO	0.1101		
Suncron Brill. Scarlet S-FW ECO	0.0506	0.06	0.79	Suncron Red S-BFW ECO	0.0551	0.01	0.30
Suncron Blue T-FW ECO	0.0005			Suncron Blue T-FW ECO	0.1260		
Suncron Yellow Brown S-FW ECO	2.0525			Suncron Yellow E-3G 200% ECO	0.0141		
Suncron Red S-BFW ECO	0.1759	0.02	0.46	Suncron Orange E-H3R 200% ECO	0.0159	0.05	0.51
Suncron Navy Blue S-FW ECO	0.0937			Suncron Blue E-FBL ECO	0.0092		
Suncron Yellow Brown S-FW ECO	1.9752			Suncron Yellow RD-E ECO	0.0557		
Suncron Brill. Scarlet S-FW ECO	0.3174	0.03	0.49	Suncron Orange H-E3R 200% ECO	0.0159	0.04	0.45
Suncron Blue S-FWN ECO	0.0992			Suncron Blue RD-E ECO	0.0107		
Suncron Yellow S-FW ECO	0.6804			Suncron Yellow S-FW ECO	0.5614		
Suncron Red S-2BSN 150% ECO	0.8835	0.04	0.42	Suncron Red S-BFW ECO	0.2091	0.03	0.50
Suncron Blue S-FWN ECO	0.0542			Suncron Navy Blue S-XFW ECO	0.3336		
Suncron Yellow Brown T-FW ECO	2.0274			Suncron Yellow T-FW ECO	0.1237		
Suncron Red CBN ECO	2.5668	0.08	0.72	Suncron Yellow Brown T-FW ECO	1.7157	0.02	0.28
Suncron Blue S-FWN ECO	0.0537			Suncron Blue S-FWN ECO	0.4446		

Mykonos Blue
18-4434

Illuminating
13-0647

Leprechaun
18-6022

Fuchsia Fedora
18-2330

Pale Rosette
13-1716

Adobe
17-1340

Fire Whirl
18-1453

Rhodonite
19-3838

Spring Lake
18-4221

Root Beer
19-1228

Coconut Cream
11-1007

Ultimate Gray
17-5104

Soybean
13-0919

Olive Branch
18-0527